

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
15 December 2005 (15.12.2005)

PCT

(10) International Publication Number  
**WO 2005/119704 A1**

- (51) International Patent Classification<sup>7</sup>: **H01B 3/44**, 7/295, 7/02
- (21) International Application Number: PCT/US2005/015618
- (22) International Filing Date: 5 May 2005 (05.05.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
60/568,317 5 May 2004 (05.05.2004) US
- (71) Applicant (for all designated States except US): **UNION CARBIDE CHEMICALS & PLASTICS TECHNOLOGY CORPORATION** [US/US]; 39 Old Ridgebury Road, Danbury, CT 06817-0001 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **JOW, Jinder** [US/SG]; 15 Ardmore Park, Number 18-03, Singapore 259959 (SG). **COGEN, Jeffrey, M.** [US/US]; 6 Braintree Court, Flemington, NJ 08822 (US).
- (74) Agent: **HANSBRO, Kevin, R.**; The Dow Chemical Company, Intellectual Property Section, P.O. Box 1967, Midland, MI 48641-1967 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- with international search report
  - before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FLAME RETARDANT PLENUM CABLE

(57) Abstract: For a flame retardant cable, it has been surprisingly found that an insulated conductor, having at least two insulation layers, a composite dielectric constant less than or equal to 2.6, and a composite dissipation factor less than or equal to 0.005, can be prepared even though one of the insulation layers has a dielectric constant greater than 2.6 or a dissipation factor greater than 0.005. It has also been surprisingly found that an insulated conductor, having a composite dielectric constant less than or equal to 2.6 and a composite dissipation factor less than or equal to 0.005, can be prepared with a non-halo-enated polyolefin as an insulation layer polymer, where the polyolefin having relatively poor dielectric/dissipative properties and the insulation layer composition being substantially free of halogenated or antimony trioxide flame retardant additives.

WO 2005/119704 A1